

# **Torrefaction of Biomass to Enhance Fuel Properties**

**By**

**Bimal Acharya**

**and**

**Animesh Dutta**

**School of Engineering, University of Guelph**

**April 20, 2013**

# Contents of Presentation

- Introduction
- Objectives
- Methodology
- Experimental Setup
- Result and Analysis
- Applications
- Conclusions
- Recommendations
- References

# Introduction


Depleting fossil fuel resources and GHG/Global Warming



Renewable energy, sustainable fuels



**Biomass** ➔ Carbon-neutral,  
local fuel; energy security





Technology barriers to their utilization as  
energy source




**Torrefaction**

# Introduction<sup>2</sup>






# Introduction<sup>1</sup>



# Objectives

- Study of Different characterizations of Lignocellulosic and Non-lignocellulosic biomass from Ontario before and after torrefaction.
- Optimization of torrefied conditions based on hydrophobicity
- Investigation of pelletization potential before and after torrefaction
- Ash analysis of biomass at different combustion temperature.


# Methodology






# Experimental Set up (Drying + Proximate)

- Apparatus:
  - Programmable Muffle Furnace
  - Thermocouple with stainless steel probe
  - Crucible
  - Desiccator
  - Weighing Balance



# Experimental Set up (Torrefaction)




# Experimental Set up (Torrefaction)

## Apparatus:

- Locally designed and fabricated Reactor
- Connecting cables and fittings
- N2 gas
- Gas Analyzer
- Preheater
- Gas Flow Meter
- Thermocouples
- Temperature Controllers (2)
- Desiccator
- Electric weigh balance




# Experimental Set up (Pelletization)




# Experimental Result (Proximate analysis)

**Comparative Study of Mass Yield at different Temp with 0% O<sub>2</sub>**




# Experimental Result (Proximate analysis)




# Experimental Result (Ultimate Analysis)

## Ultimate Analysis Results




# Experimental Result (HHV)






# Experimental Result (Hydrophobicity-All)


## Comparative Study of Hydrophobicity




# Experimental Result (Moisture Uptake-all)



# Experimental Result (Pelletization-Making)




# Experimental Result (Pelletization-Breaking)




# Experimental Result (Ash Fusion Temp)

Ash Fusion Temperature of Poultry Litter, Willow and Oat Pallets




# Experimental Result (Elemental Ash Analysis)

## Elemental Ash Analysis of Poultry Litter, Willow and Oat Pellets



# Experimental Result (Ash Fusion Temperature)

Ash Fusion Temperature of Poultry Litter, Willow and Oat Pallets



# Applications

## Residential and commercial heating

## Power generation

- Biomass Co-firing in large scale coal-fired power plants
- Competes with coal in terms of price as well as performance
- Higher co-firing rates possible (compared to biomass)
- Most practical option to meet provincial mandate to phase out coal by 2014

## Steel production

- TB with LHV in the range of 25 MJ/kg required

## Biomass-to-liquid fuel

- Transportation fuels (Fischer–Tropsch process)

## Export

- Large markets exist in US & Europe



# Conclusions

|               | Coal    | Torrefied Pellets |
|---------------|---------|-------------------|
| Heating Value | 25 GJ/T | 22 GJ/T           |
| Ash           | 10%     | 3%                |
| Sulphur       | 3%      | 0.1%              |
| Nitrogen      | 1.5%    | 0.2%              |
| Chlorine      | 0.05%   | 0.01%             |

- Torrefied biomass can be used for co-firing with coal in thermal power plant, heating system and combustion system.

# Conclusion

| Characterization   | Lignocellulosic        | Non-Lignocellulosic       |
|--------------------|------------------------|---------------------------|
| 1. Mass Yield      | Fast                   | Slow                      |
| 2. Energy Yield    | High                   | Low                       |
| 3. Hydrophobicity  | Yes                    | Yes                       |
| 4. Moisture Uptake | Low                    | High                      |
| 5. Pelletization   | Possible               | Possible only with binder |
| 6. HHV             | High 20-24MJ/Kg        | Low 12MJ/Kg               |
| 7. Ash Composition | High Silica components | High Calcium component    |
| 8. Ash Fusion      | Low 1100-1200°C        | High 1400°C               |

# Recommendations

- Try to use torrefied biomass pellets for co-firing with coal in thermal power plant, heating system and combustion system.
- Run small businesses for pellet making: Raw and Torrefied both
- Need to explore further on economic viability and sustainability of the technology

# References

1. Acharya B., Sule I. & Dutta A. (2012). A review on advances of torrefaction technologies for biomass processing, Biomass Conversion and Biorefinery, December, Volume 2, [Issue 4](#), pp 349-369.
2. Uslu A., Faaij A.P.C., and Bergman P.C.A., (2008) "Pre-treatment technologies, and their effect on international bioenergy supply chain logistics. Techno-economic evaluation of torrefaction, fast pyrolysis and pelletization", Elsevier Energy Vol. 33, pp 1206–1223
3. Kiel J.H.A., F. Verhoeff, H. Gerhauser and B. Meuleman (2008) BO2 Technology for Biomass Upgrading into solid fuel-Pilot Scale Testing and Market Implementation; Energy research Centre of the Netherlands (ECN), P.O. Box 1755 ZG Petten, the Netherlands.
4. Kleinschmidt C.P.,(2011) "Overview of international developments in torrefaction," Bio-energy Trade, Torrefaction workshop, January, [online material]URL:  
<http://www.bioenergytrade.org/downloads/grazkleinschmidtpaper2011.pdf>
5. Tumuluru J.S., Sokhansanj S, Hess J.R., Wright C.T., and Boardman R.D.; (2011) "A review on biomass torrefaction process and product properties for energy applications, Industrial Biotechnology, October.
6. Felfli F.F., Luengo C.A., Soler P.B., and Rocha J.D.,(2004) "Mathematical Modelling of Woods and Briquettes Torrefaction, Proceedings of the 5th Encontro de Energia no Meio Rural, Campinas, Spain, October 19–2 <http://www.feagri.unicamp.br/energia/agre2004/Fscommand/PDF/Agrener/Trabalho%205.pdf>
7. Bridgeman T.G., Jones, J.M., Shield, I., and Williams P.T., (2008), "Torrefaction of reed canary grass, wheat straw and willow to enhance solid fuel qualities and combustion properties," Journal of Fuels, Vol. 87, pp. 844 – 856.
8. Bergman PCA, Boersma AR, Zwart RWH, and Kiel JHA (2005). *Torrefaction for biomass co-firing in existing coal-fired power stations. Report ECN-C--05-013, ECN.*

.....

# Thank you

## Any Questions ?